



**TRE EMME** S.p.A.  
MANIFATTURA MARCHIGIANA MACERATA  
Via Dell'Artigianato, 22  
62020 S. ANGELO IN PONTANO (MC) - ITALY  
Iscr. Reg. Soc. MC N. 5227 - CCIAA MC N. 100692  
Tel. +39 0733.663334/663316/663416 - Fax +39 0733.663417  
CAP. SOC. Euro 120.000,00 - P. IVA 00860500438  
<http://www.treemme.net> - e-mail: [treemme@treemme.net](mailto:treemme@treemme.net)  
V.A.T. reg. IT 00860500438



## TECHNICAL DATA SHEET

### ADHESIVE TAPE: PACK LOW NOISE

#### FILM PROPERTIES

TYPE OF FILM	BIAXIALLY ORIENTED POLYPROPYLENE
FILM COLOUR	TRANSPARENT
FILM THICKNESS (MICRON)	28 (+/-1)
TENSILE STRENGTH MD (N/mm <sup>2</sup> )	140 (+/-30)
ELONGATION AT BREAK MD (%)	140 (+/-30)

#### ADHESIVE PROPERTIES

TYPE OF ADHESIVE	ACRYLIC (WATER BASED)
COLOUR	TRANSPARENT/BROWN
PEEL ADHESION (N/25mm)	5.5 (+/-1)
SHEAR ADHESION (h, 25mm X 25mm on STAINLESS STEEL, 23°C)	OVER 170
ROLLING BALL TACK (cm)	3

The recommended storage conditions for this product are around 21°C and 50% relative humidity. Prior to use, carefully check that the contact surfaces are totally dry and clean from oil, grease or dust. The data stated above cannot be considered as binding by contract or by specifications. They correspond to the average values obtained from the tests carried out in conformity with AFERA norms. Tests are carried out on samples taken from our standard production. These data may vary without notice – the updated typical value sheet can be forwarded at any time.

Since many different factors influence the product's performance, we recommend testing the product by any application. We remain at your disposal for any further information or recommendations.

07/01/2011